



Specification

Zeon Chemicals L.P.
4100 Bells Lane
Louisville, KY 40211
www.zeonchemicals.com

Date Issued: 02/20/2013

Supersedes: 10/03/2007

Product Name: Zeotherm 131-90B

Product Description: Zeotherm 131-90B is a high-performance thermoplastic vulcanizate (TPV) designed to survive long-term exposure to 150°C air and oil. This grade is optimized for blow molding processes.

Product Packaging: Standard unit is a 50-lb foil-lined paper bag.

Specifications

No	Product Characteristic	Procedure	Property	Unit	Specifications	
					Min	Max
1	Hardness, Shore A (15s delay)	PT-004	Hardness	pts	87	97
2	Specific Gravity	PT-029	Specific Gravity	N/A	1.09	1.15
3	Bulk Density	ASTM D1895	Density	lb/ft ³	28.00	38.00
4	Elongation	PT-006B	Eb	%	175	-
5	Melt Flow Index	PM-026	MFI	g/10 min	2.00	8.00
6	Tensile Strength	PT-006B	Tb	MPa	11.00	-

Special Notes

FDA Information: For specific information, please make an inquiry to productstewardship@zeonchemicals.com.

SDS Disclaimer: Refer to the appropriate SDS for safety, handling and storage instructions.

Test Proc. Disclaimer: Zeon Test Procedures available upon request.

Change Notification: No significant change in manufacturing site location, raw material(s), raw material supplier(s), testing methods, test equipment, test facilities, manufacturing location, manufacturing process, and / or manufacturing equipment shall occur without notification.

Shelf Life: Retest critical parameters 2 years after date of manufacture.

Other Notes: Measured on injection molded specimens.

Revision Summary: 1.) Update format. 2.) Update Shelf Life.

The information contained herein is believed to be reliable, but no representations, guarantees or warranties of any kind are made as to its accuracy, suitability for particular applications or the results to be obtained there from. The information is based on laboratory work with small-scale equipment and does not necessarily indicate end product performance. Because of the variations in methods, conditions and equipment used commercially in processing these materials, no warranties or guarantees are made as to the suitability of the products for the applications disclosed. Full-scale testing and end product performance are the responsibility of the user. Zeon Chemicals L.P. shall not be liable for and the customer assumes all risk and liability of any use or handling of any material beyond the direct control of Zeon Chemicals L.P. The SELLER MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OR MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Nothing contained herein is to be considered as permission, recommendation, nor as an inducement to practice any patented invention without permission of the patent owner.