



Specification

Zeon Chemicals L.P.
4100 Bells Lane
Louisville, KY 40211
www.zeonchemicals.com

Date Issued: 10/20/2015

Supersedes: 07/08/2014

Product Name: Zetpol 2000EP

Product Description: Zetpol 2000EP is an easy processing, highly saturated copolymer of butadiene and acrylonitrile with high tensile strength, excellent heat resistance, good chemical resistance to aggressive fluids, and an excellent balance of properties over a wide variati of temperatures.

Product Packaging: Zetpol 2000EP shall be in the form of dark amber/black-brown colored 25 kg (55.1 lb) bales free from foreign material considered objectionable for normal applications.

Specifications

No	Product Characteristic	Procedure	Property	Unit	Specifications	
					Min	Max
1	Bound ACN	ZCI-T-010/NZ:R142	Content	%	34.90	37.50
2	Ash Content	ZCI-T-005/NZ:R100	Content	%	-	1.90
3	Heat Loss	ZCI-T-002/NZ:R001	Loss	%	-	1.00
4	Iodine Value	ZCI-T-004/NZ:R133	Value	mg/100 mg	-	9.00
5	Mooney Viscosity (ML1+4/100°C)	ZCI-T-003/NZ:R007	Viscosity	MU	23.0	37.0

Special Notes

FDA Information: For specific information, please make an inquiry to productstewardship@zeonchemicals.com.

SDS Disclaimer: Refer to the appropriate SDS for safety, handling and storage instructions.

Test Proc. Disclaimer: Zeon Test Procedures available upon request.

Change Notification: No significant change in manufacturing site location, raw material(s), raw material supplier(s), testing methods, test equipment, test facilities, manufacturing location, manufacturing process, and / or manufacturing equipment shall occur without notification.

Shelf Life: Retest critical parameters 3 years after date of manufacture.

Revision Summary: 1.) Update Iodine Value Max from 7.0.

The information contained herein is believed to be reliable, but no representations, guarantees or warranties of any kind are made as to its accuracy, suitability for particular applications or the results to be obtained there from. The information is based on laboratory work with small-scale equipment and does not necessarily indicate end product performance. Because of the variations in methods, conditions and equipment used commercially in processing these materials, no warranties or guarantees are made as to the suitability of the products for the applications disclosed. Full-scale testing and end product performance are the responsibility of the user. Zeon Chemicals L.P. shall not be liable for and the customer assumes all risk and liability of any use or handling of any material beyond the direct control of Zeon Chemicals L.P. The SELLER MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OR MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Nothing contained herein is to be considered as permission, recommendation, nor as an inducement to practice any patented invention without permission of the patent owner.